



120/150 Penetration Grade Bitumen / Asphalt Cement

120/150 is the softest penetration grade in the Pro-Road Global range. It keeps its flexibility in cold climates and at high altitude. It resists low-temperature cracking.

Typical applications

- Roads in cold and high-altitude regions
- Pavements where thermal cracking governs design
- Base binder for emulsions in cold regions

Packaging for export

- New steel drums, 150 kg to 200 kg
- Big bags (bitu-bags), 250 kg to 1,200 kg
- Bitutainers for regular bulk volumes

Specifications

Property	Test Method (BS EN)	Test Method (AASHTO)	Specification
Penetration at 25°C (0.1 mm)	BS EN 1426	AASHTO T 49	120-150
Softening Point (°C)	BS EN 1427	AASHTO T 53	35-45
Ductility at 25°C (cm)	BS EN 13589/BS EN 13398	AASHTO T 51	Minimum 100
Flash Point (°C)	BS EN ISO 2592	AASHTO T 48	Minimum 230
Solubility in Trichloroethylene (%)	BS EN 12592	AASHTO T 44	Minimum 99.0
Specific Gravity at 25°C	BS EN 15326	AASHTO T 228	1.01-1.06
Loss on Heating (wt%)	BS EN 12607-1	AASHTO T 47	Maximum 0.5
Residue Penetration after Heating (%)	BS EN 1426	AASHTO T 49	Minimum 55
Kinematic Viscosity at 135°C (mm ² /s)	BS EN 12595	AASHTO T 201	350-450
Fraass Breaking Point (°C)	BS EN 12593	AASHTO T 314	Maximum -5
Storage Stability (Difference in Softening Point, °C)	BS EN 13399	AASHTO T 316	Maximum 2

Values shown are typical specifications under BS EN and AASHTO test methods. Request the certificate of analysis for your batch at the time of order.

Request a quote: info@proroadglobal.com · www.proroadglobal.com